



SPECIALTIES FOR MAINTENANCE
& SANITATION SINCE 1947

LATER GATOR

FM 3341

- EASE OF APPLICATION
- POURABLE FORMULA
- MINIMAL SURFACE PREPARATION
- LEVELS TO GRADE EASILY
- REDUCED CLOSURE TIME

SPECIFICATIONS

- ADVANCED POLYURETHANE POLYMERS
- COLD WEATHER ACCELERANT INCLUDED
- IMPERVIOUS TO FUEL
- EXCEPTIONAL BINDING PROPERTIES
- EXCELLENT EDGE STRENGTH



LATER GATOR KIT

VERSATILE – Alligatoring, Cracks, Potholes, Cold Joints, Uneven Grades, Rutting & Block Cracking

APPLICATION QUALITIES– Superior Adhesion, Waterproofs, No Compaction Required, Excellent Surface Quality & **Cures Quickly**

UTILIZE IN ANY TEMPERATURE – 1 ounce of accelerant included for applications below 50°F. **Do not use accelerant in warmer temperatures to avoid premature curing.**

MIX THOROUGHLY – Use a powerful drill with FM 9533 Mixing Tool bit to ensure adequate mixing



FM 9533 MIXING TOOL



DEMO VIDEO

**ALL COMPONENTS CONVENIENTLY
PACKAGED IN A 5 GAL PAIL**



Contact Us



1.800.238.5150
1.901.375.3600



sales@deltaforemost.com
deltaforemost.com



3915 Air Park Street
Memphis, TN 38118



TECHNICAL DATA

FOREMOST 3341-ES LATER GATOR

Rev. 3-25-21

- DESCRIPTION:** A polymer-modified liquid and aggregate slurry that hardens in minutes, providing a permanent repair without the need for extensive surface preparation. Damaged areas can be returned to traffic in a fraction of the time required for traditional repair methods. The polymer-based repair works in areas subject to movement or damaged base. Perfect for areas not accessible to heavy asphalt working equipment. Achieves results where ordinary asphalt repair materials fail.
- APPLICATION:** FM-3341 Later Gator is a cost-effective alternative to traditional spall repair, driveway asphalt repair, floor repair and other asphalt restoration procedures. Especially effective in areas lacking the depth for traditional patching procedures.
- DIRECTIONS:** **NOTE:** FM-3341 Later Gator is not a significant irritant. Nevertheless, skin or eye contact may lead to sensitization. Protective gloves and safety glasses should be worn. Wash hands after handling product before eating, drinking, or smoking. **SURFACE PREPARATION:** Remove as much loose and unsound material as possible. Total removal is not critical. Remove remaining loose debris by sweeping or using air to blow fine cracks and potholes. Apply only to dry surfaces. Moist or damp surfaces will weaken the product's ability to bond to the surface. **CAUTION: KEEP PAILS SEALED UNTIL READY-TO-USE TO AVOID MOISTURE CONTAMINATION. MIXING:** Remove 12 lb. bag of topping sand and both A and B bottles of polymer from the 5-gallon pail. Add polymer A to the 5-gallon container of coated aggregate and mix using the FM 9533 Mixing Tool drill bit for 1-2 minutes until all the aggregate is completely saturated. Next, add all of polymer B and mix thoroughly for one minute. Material should now be in the form of a pourable slurry. Working time will be approximately 10 minutes at an ambient temperature of 75°F.
- INSTALLATION:** Squeegee, screed, gauge-rake, or trowel thin slurry over repair area. The outer areas of the repair can be feathered into the existing surface with a hand trowel. Once liquid material is applied to the repair area, broadcast all 12 lbs. of topping sand evenly over the repair area.
- CURE:** Cure for one hour minimum at a temperature of 75°F, allowing approximately 30 minutes for every 5° below 75°F. For temperatures below 60°F, add ½ the vial of the supplied catalyst (1 oz). For temperatures below 50°F, add the full 1 oz. bottle of catalyst. Colder temperatures will dictate a slower cure rate.
- PACKAGING & COVERAGE:** 5-gallon kit (52 lbs.) will cover approximately 6.25 square feet at 1" depth.
- PRECAUTIONS:** **KEEP OUT OF REACH OF CHILDREN.** Causes eye irritation. Avoid contact with eyes. May cause skin irritation. **FIRST AID: IF INHALED:** Remove to fresh air. If not breathing, give artificial respiration, preferably mouth to mouth. If breathing is difficult, give oxygen and call a physician. **SKIN CONTACT:** Wash skin with soap and water. Remove contaminated clothing. **EYE CONTACT:** Flush with water; continue for at least 15 minutes. Call a physician.

Before using this product read the Safety Data Sheet (SDS) for more detailed information regarding safe handling.