



**3343**

## **FAST DRY FISSURE AND CRACK FILLER**

**SPECIALTIES FOR MAINTENANCE AND SANITATION SINCE 1947**



*Repairs Joints In Concrete Floors*

- **Pours like water to penetrate hairline cracks.**
- **Self-leveling, requires no screeding or troweling.**
- **Makes sagging floors level and flat.**
- **Hardens to resist wheeled traffic or impact from dropped objects**

### ***A Select Two (2) Component Epoxy Formulation That Offers Binding Qualities Not Found In Similar Products***

**EASY-TO-USE** — It is poured right into hairline cracks and joints to seal out destructive chemicals, water and frost.

**FLEXIBLE** — 100% epoxy joint compound. Designed to absorb shock and impact of heavy loads and steel wheels.

**DURABLE** — Hardens to a high compressive strength, impact resistance, shock resistance and vibration absorbency.

**EFFICIENT** — Self-priming, self-leveling, non-shrinking and won't become brittle.

**IMPROVES** sanitation with an impervious surface that cannot be penetrated or embedded with dirt and bacteria.

**RECOMMENDED FOR** — Fast and economical repairs to cleft or cracked, dividing or breaking concrete, sidewalks, driveways, curbs, expansion joints, steps and ledges in breweries, bottling plants, dairies, food processing plants, industrial plants, petroleum refineries and warehouses.

**Each Kit Includes:** 12-1 Gal. 3343A Epoxy Matrix & 12-1 Qt. 3343B Catalyst

Rev. 7-18-14

Toll Free: 800-238-5150  
Local: 901-363-4340  
Fax: 901-375-3600

**Delta Foremost Chemical Corp.**  
3915 AIR PARK ST. • P.O. BOX 30310 • MEMPHIS, TENNESSEE 38130-310

Visit our Web Site at:  
[www.deltaforemost.com](http://www.deltaforemost.com)





# TECHNICAL DATA

## FOREMOST 3343 FAST DRY FISSURE AND CRACK FILLER

Rev. 11-5-15

**DESCRIPTION:** Foremost 3343 Fast Dry Fissure and Crack Filler is a select two (2) component epoxy formulation that offers binding qualities not found in similar products. Its low viscosity enables it to be poured right into hairline cracks and joints to seal out destructive chemicals, water and frost. Foremost 3343 Fast Dry Fissure and Crack Filler is self-priming, self-leveling, non-shrinking and won't become brittle. It is a 100% epoxy compound that absorbs steel wheel impact.

**APPLICATION:** Foremost 3343 Fast Dry Fissure and Crack Filler is recommended for fast and economical repairs to cleft or cracked, dividing or breaking concrete, sidewalks, driveways, curbs, expansion joints, steps and ledges in breweries, industrial plants, food processing plants, petroleum refineries and warehouses.

**DIRECTIONS:** **NOTE:** Do not contaminate material with water before applying. Do not apply out of doors if rain is likely. Do not apply if the temperature of the surface is below 55°F.

1. Surface to be coated should be cleaned and free from oil and grease. Sweep thoroughly to remove dirt and loose debris.
2. Mix together, using metal container, one part of Part B Catalyst to 4 parts of Part A Epoxy Matrix or one (1) quart of Part B Catalyst to one (1) gallon of Part A Matrix. Do not mix together more material than will be needed to complete the job at hand. Continue mixing till the solution is free of swirls and streaks. Use material immediately.
3. Immediately pour mixture into cracks, holes, joints, etc. Fast Dry Fissure and Crack Filler is normally self-leveling but may be smoothed if necessary with normal cement working tools.
4. Tools can be cleaned with detergent and water if they are cleaned immediately after use. Do not allow product to cure on tools or in dispensing equipment.
5. The time necessary for curing is highly dependent upon temperature. Optimum conditions allow curing in approximately 4 hours for foot traffic. Cooler temperatures will significantly slow the curing rate of FM 3343. Under some conditions it may take as long as 24 hours for a complete cure, especially if heavy traffic, such as fork lifts, is anticipated.
6. **NOTE:** This product gets **HOT** as it cures. Use as quickly as possible after complete mixing. Take appropriate safety measures.

**THE POT LIFE OF THIS MIXTURE IS APPROXIMATELY 20 MINUTES. DO NOT MIX MORE MATERIAL THAN CAN BE APPLIED WITHIN 15 MINUTES.**

**PRECAUTIONS:** **KEEP OUT OF REACH OF CHILDREN.** Avoid contact with face, skin or eyes. May cause skin irritation. May be harmful if swallowed. Do not take internally.

**FIRST AID: EYES:** Flush eyes with plenty of water for at least 15 minutes. Get medical attention. **SKIN:** Wash with soap and water. Get medical attention if irritation occurs. Remove and wash contaminated clothes. **INGESTION:** If swallowed, induce vomiting. If large amounts are ingested, see physician immediately.

Before using this product, read the Safety Data Sheet (SDS) for more detailed information regarding safe handling.